

TeraPrint Produktunterlage

Gebrandete TeraPrint-Downloadunterlage

PRODUKT	Akylite® (Plex)
UNTERLAGE	Datenblatt Akylite
TYP	datasheet
ORIGINALSEITEN	2
STAND	16.06.2026
DATEI	products/2024-akylite/assets/documents/4b5bc96473de14ee802104a97ba053c4eb4b93f3439ddd44e08167b6234789dd.pdf

Wichtig fuer die Produktion


Die folgenden Originalseiten bleiben in Format, Reihenfolge und Inhalt unveraendert.
Druckmass, Schnitt, Beschnitt, Sicherheitsbereiche und technische Vorlage wurden nicht veraendert.
Bei Zertifikaten, Datenblaettern und Pruefberichten bleiben Aussteller und Originalinhalte unveraendert.

TeraPrint Hinweis

Diese Datei ist lokal bei TeraPrint gespeichert und fuer den Kunden-Download vorbereitet.
Bitte bei Druckdaten immer die Massangaben und Beschnitt-/Sicherheitszonen der Originalvorlage beachten.
Bei Unsicherheit vor Bestellung oder Produktion TeraPrint kontaktieren.

TECHNICAL SPECIFICATION

AKYLITE® 2.9mm 600 g/m²



► Description : bubble structure polypropylene copolymer extruded

Product	Treatment *	Thickness (mm)	Weight gr/sqm	Density	Colour
Akylite®	Corona	2.9 ± 0.2	600±60	0.21	white

*others on request

Description	Diameter (mm)	Colour
Bubbles	4	White or translucent

► Item

	Dimension (mm)	Tolerance
Width	2050	+/- 2 mm
Length	3050	0/+16 mm
Squareness		3 mm / m

► Logistic details

Nr of piece/pallet	150
Dimension of pallet	2050 x 3050 x 585
Protection	Wood pallet + SPC bottom and cover + PP Corners + PE stretch foil
Storage	Inside, dry place, 2 pallets on 1 maxi

► Treatment

	Method	Unit	Value	Result
Corona	Sherman pens	mN/m	≥ 38	6 months
Anti-static	On request			
Fire retardant	On request			
UV treatment	On request			

► Printing

	2 sides	1 side
Silkscreen UV		X
Digital UV		X

In order to protect better the printing results, we recommend to apply an additional varnish over the inks.

► Converting

- Gluing (hot melt: PP or polyurethane reactive)
- Welding
- Screwing
- Riveting
- Stapling
- Cutting (guillotine, die cut, laser, knife, plotter)
- Folding (hot or cold)

► Regulations

- Conformity with: Heavy metal (RoHS, 94/62/EC); REACH / SVHC; ELV (n°2000/53/CE)
- Food contact: please consult us

▶ Mechanical properties of raw material*

Property	Method	Unit	Result
Tensile Strength at Yield	ISO 527-2	M Pa	25
Elongation at Yield	ISO 527-2	%	7
Flexural modulus	ISO 178	MPa	1100
Izod Impact Strength			
At 23°C	ISO 180	KJ /m ²	18
At -20°C			5.5
Melt Flow Index 230°C/2.16kg	ISO 1133	g/10min	3.5

▶ Mechanical properties of final product

Property	Method	Unit	Result
Flexural Break Resistance (Distance between fulcrums: 100 mm, test speed 5 mm/m, sample: 40x200 mm)	ISO 178	N/mm ²	> 4.0
Compression Resistance	ISO 3035	%	< 30
Deformation by 1000 kPa Pressure			
Dimensional variation 22H, 70°C	Internal	%	< 0.5
Impact resistance at -30° C and 23 °C (steel ball 500 g, falling height: 250 mm)	Internal		no effect

▶ Thermal properties of raw material*

Property	Method	Unit	Result
Melting point	ISO 3146	°C	165
Heat Deflection Temperature			
1.80 MPa – 120°C per hour	ISO 75-2	°C	50
0.45 MPa - 120°C per hour			92
Flash point		°C	350
Auto ignition temperature		°C	> 380
Thermal expansion coefficient		mm/m°C	0,11

*Extracted from the polypropylene Heterophasic Copolymer raw material data sheet

▶ Chemical resistance

Polypropylene has good chemical inertness and good resistance to cracking under stress. It has no solvent at 20°C. Very resistant to mineral and organic products; it is neither affected by water solutions of mineral salts, nor by chemical bases and mineral acids at temperatures lower than 60°C, except very strong acids. Not resistant to substances with an oxidizing effect or to certain solvents. Details can be supplied on request.

▶ Environment

Polypropylene is persistent in the environment and is not biodegradable.

▶ Recycling properties

▶ Thermal recycling or incineration

The heat produced can then be used as substitutes for oil, gas and coal or to generate energy at power plants.

The complete combustion of polypropylene with air only produces carbon dioxide and water. At higher temperatures traces of nitrogen oxide are present.

The incomplete combustion of polypropylene produces soot, carbon dioxide and monoxide, and several carbon, hydrogen and oxygen compounds. Unburnt substances or additional products may be released.

The same by-products are also released during the combustion of natural materials such as wood or wool.

▶ Mechanical recycling

Polypropylene wastes can easily be recycled. They are collected, separated, milled, melted and extruded in granules in order to be re-injected in our process. We can reuse our own wastes and also the wastes of our customers.

▶ Complementary information:

Industrial waste number EC for PP: plastics (16 10 19, 17 02 03 & 20 01 39)



www.kaysersberg-plastics.com