

TeraPrint Produktunterlage

Gebrandete TeraPrint-Downloadunterlage

PRODUKT	Aufkleberbogen
UNTERLAGE	Datenblatt Ultra Destructible
TYP	datasheet
ORIGINALSEITEN	2
STAND	16.06.2026
DATEI	products/2025-stickersheet/assets/documents/261ef0ea1127e23c34b2aa3d2c330d61eca7e7f8ad378b73e245a087db45d950.pdf

Wichtig fuer die Produktion

Die folgenden Originalseiten bleiben in Format, Reihenfolge und Inhalt unveraendert.
Druckmass, Schnitt, Beschnitt, Sicherheitsbereiche und technische Vorlage wurden nicht veraendert.
Bei Zertifikaten, Datenblaettern und Pruefberichten bleiben Aussteller und Originalinhalte unveraendert.

TeraPrint Hinweis

Diese Datei ist lokal bei TeraPrint gespeichert und fuer den Kunden-Download vorbereitet.
Bitte bei Druckdaten immer die Massangaben und Beschnitt-/Sicherheitszonen der Originalvorlage beachten.
Bei Unsicherheit vor Bestellung oder Produktion TeraPrint kontaktieren.

UPM Raflatac Technical Information

05-01-2023 EN SI

Product	ACRYLATE WHITE UD TC / RC18 / HD 70
Sales Code	FXH/RC18/28
EAN	6415788261095
Product use	Product designed for security labeling applications when tamper-evident features are required. With its brittle face material characteristics, this white product, is difficult to remove in one piece without visible evidence of the tampering, once adhered.

Typical technical values

Face		ACRYLATE WHITE UD TC			
Product	A white, top coated, satin finish, acrylate film with low elongation at break.				
Substance	70	g/m²	ISO 536		
Caliper	51	µm	ISO 534		
Tensile strength MD	67	MPa	ISO 527/3		
Elongation at break MD	6	%	ISO 527	max.	
Printability	Suitable for UV flexo, UV screen and UV letterpress; other methods should be tested.				
Adhesive		RC18			
Type	Strong permanent				
Composition	UV-acrylic				
Tack	20	N/25mm	FTM 9	(on glass)	
Peel 180°	23	N/25mm	FTM 1	(on glass)	
Backing		HD70			
Product	A white transparent glassine backing paper.				
Substance	62	g/m²	ISO 536		
Caliper	54	µm	ISO 534		
Tensile strength MD	7	kN/m	ISO 1924		
Tensile strength CD	2,7	kN/m	ISO 1924		
Transparency	48	%	DIN 53147		
Performance					
Total caliper	130				
Minimum labelling temperature	5 °C				
Service temperature	-20 °C to 100 °C				
Shelf life	From date of manufacture: 12 months, under FINAT defined storage conditions (+20-25°C and RH 40-50%). Prolonged storage at higher temperatures and/or humidity levels will shorten the shelf life.				
Information					
Product Information	It takes from several hours to days for the adhesive to develop its full tamper evident functionality.				

Additional info

Label corners should have a larger radius than normal (minimum 3mm). Matrix removal should take place directly after die-cutting to prevent adhesive "flowing" back, using large diameter roller, not a blade. Experience shows that higher machine speeds (compared to PVC White UD) are possible, with 3mm label gaps and 5mm radius corners. In general this product is suitable for manual and automatic dispensing. We recommend to validate the functionality under original conditions. The face destruction when an attempt to remove the label is made, requires a specific adhesion to the substrate and is typically of a tearing type. To assist the tearing of the face film when applied to polar surfaces, security slits should be added. We recommend considering all parameters that can influence the adhesion, namely substrate, temperature, application pressure and dwelling time.

Disclaimer

The performance of the product should always be tested in the actual application conditions. Our recommendations are based on our most current knowledge and experience. As our products are used in conditions beyond our control, we cannot assume any liability for damage caused through their use. Users of our products are solely responsible that the product is suitable for its intended application, and have determined such at their sole discretion. Users must comply with any applicable legislation and/or testing requirements for the finished article, and are responsible for bringing their products to market.

This publication does not constitute any warranty, express or implied, and is intended only for the recipient and cannot therefore be transferred to any third party. We cannot assume any liability for the use of our products in conjunction with other materials.

All our products are sold subject to UPM Raflatac's general sales conditions, and you should ensure that any existing laws are observed.

This publication replaces all previous versions. All information is subject to change without notice.

