

TeraPrint Produktunterlage

Gebrandete TeraPrint-Downloadunterlage

PRODUKT	Aufkleberbogen
UNTERLAGE	Datenblatt Papier glanz
TYP	datasheet
ORIGINALSEITEN	2
STAND	16.06.2026
DATEI	products/2025-stickersheet/assets/documents/7028165526682119df9b4593a6044aa3aba27502466ac2877db7817d4d9cebef.pdf

Wichtig fuer die Produktion

Die folgenden Originalseiten bleiben in Format, Reihenfolge und Inhalt unveraendert.
Druckmass, Schnitt, Beschnitt, Sicherheitsbereiche und technische Vorlage wurden nicht veraendert.
Bei Zertifikaten, Datenblaettern und Pruefberichten bleiben Aussteller und Originalinhalte unveraendert.

TeraPrint Hinweis

Diese Datei ist lokal bei TeraPrint gespeichert und fuer den Kunden-Download vorbereitet.
Bitte bei Druckdaten immer die Massangaben und Beschnitt-/Sicherheitszonen der Originalvorlage beachten.
Bei Unsicherheit vor Bestellung oder Produktion TeraPrint kontaktieren.

UPM Adhesive Materials Technical Information

04-12-2025 EN SI EMEIA

Product	RAFLACOAT PLUS-FSC RP51 HONEY GLASSINE 65-FSC
Sales Code	FLK/RP5X/FUX
EAN	6415788464243
Product use	Product designed for general purpose high quality multicolor printed labels to packaged food and homecare applications in ambient conditions. Suitable also for logistics labelling in case that the end user is looking for mid gloss appearance.

Typical technical values

Face	RAFLACOAT PLUS-FSC		
Product	White woodfree machine coated mid-gloss paper.		
Substance	77	g/m ²	ISO 536
Caliper	67	µm	ISO 534
Tensile strength MD	5	kN/m	ISO 1924/1
Tensile strength CD	2,4	kN/m	ISO 1924/1
Brightness	89	%	ISO 2470/1
Roughness	1	µm	ISO 8791 PPS 10
Opacity	86	%	ISO 2471
Gloss	66	%	Hunter 75°
CIE Whiteness	120	%	ISO 11475
Stiffness MD	0,23	mNm	ISO/DP 2493
Stiffness CD	0,13	mNm	ISO/DP 2493
Printability	Suitable for flexography, offset, rotogravure, screen and hot foil. Suitable for thermal transfer printing with wax/resin ribbons. Testing recommended.		
Sustainability	The product is sold as FSC Mix Credit under UPM Raflatac's FSC™ certificate SGSCH-COC-004879.		

Adhesive	RP51
Type	General purpose permanent adhesive.
Composition	Acrylic, water borne.
Tack	18 N/25mm FTM 9

Backing	HONEY GLASSINE 65-FSC
Product	Yellow transparent glassine backing paper.
Substance	54 g/m ² ISO 536
Caliper	47 µm ISO 534

Tensile strength MD	5,4	kN/m	ISO 1924
Tensile strength CD	2,2	kN/m	ISO 1924
Transparency	49	%	DIN 53147
Sustainability	The product is sold as FSC Mix Credit under UPM Raflatac's FSC™ certificate SGSCH-COC-004879.		

Performance

Total caliper	132 µm ± 10%
Minimum labelling temperature	0 °C
Service temperature	-20 °C to 80 °C
Shelf life	From date of manufacture: 48 months, under FINAT defined storage conditions (+20-25°C and 40-50% RH). Prolonged storage at higher temperatures and/or humidity levels will shorten the shelf life.

Information

Product Information	Good adhesion to all normal substrates, including non-polar surfaces, films, and corrugated board. Good low temperature performance. Not recommended for labelling highly curved surfaces.
---------------------	--

Approvals

Approvals	For further compliance information related to food labeling applications, please contact your local sales representative for a Declaration of Conformance (DoC) document.
-----------	---

Disclaimer	The performance of the product should always be tested in the actual application conditions. Our recommendations are based on our most current knowledge and experience. As our products are used in conditions beyond our control, we cannot assume any liability for damage caused through their use. Users of our products are solely responsible that the product is suitable for its intended application, and have determined such at their sole discretion. Users must comply with any applicable legislation and/or testing requirements for the finished article, and are responsible for bringing their products to market.
------------	---

This publication does not constitute any warranty, express or implied, and is intended only for the recipient and cannot therefore be transferred to any third party. We cannot assume any liability for the use of our products in conjunction with other materials.

All our products are sold subject to UPM Raflatac's general sales conditions, and you should ensure that any existing laws are observed.

This publication replaces all previous versions. All information is subject to change without notice.

