

TeraPrint Produktunterlage

Gebrandete TeraPrint-Downloadunterlage

PRODUKT	Aufkleberbogen
UNTERLAGE	Datenblatt weißes stark haftendes
TYP	fire_certificate
ORIGINALSEITEN	1
STAND	16.06.2026
DATEI	products/2025-stickersheet/assets/documents/b879a53725b238eb00cde5cb19fcdb8ba24270a8eb7e5bac73f31d054b8adab9.pdf

Wichtig fuer die Produktion

Die folgenden Originalseiten bleiben in Format, Reihenfolge und Inhalt unveraendert.
Druckmass, Schnitt, Beschnitt, Sicherheitsbereiche und technische Vorlage wurden nicht veraendert.
Bei Zertifikaten, Datenblaettern und Pruefberichten bleiben Aussteller und Originalinhalte unveraendert.

TeraPrint Hinweis

Diese Datei ist lokal bei TeraPrint gespeichert und fuer den Kunden-Download vorbereitet.
Bitte bei Druckdaten immer die Massangaben und Beschnitt-/Sicherheitszonen der Originalvorlage beachten.
Bei Unsicherheit vor Bestellung oder Produktion TeraPrint kontaktieren.

UPM Raflatac Technical Information

23-06-2025 EN SI EMEA

Adhesive	RH1
Sales Code	RH01
Type	Permanent
Composition	Hotmelt
Use	Designed for use in cold environment, moist surface when very high initial adhesion is required. Good low temperature performance once labelled. Very good adhesion to non-polar surfaces. Good adhesion to cardboard in chill and freezer conditions.

Typical technical values

Tack	25	N/25mm	FTM 9
Labelling temperature min	-5	°C	
Service temperature min	-40	°C	
Service temperature max	50	°C	

Limitations Use on highly curved surfaces needs pretesting.

Disclaimer The performance of the product should always be tested in the actual application conditions. Our recommendations are based on our most current knowledge and experience. As our products are used in conditions beyond our control, we cannot assume any liability for damage caused through their use. Users of our products are solely responsible that the product is suitable for its intended application, and have determined such at their sole discretion. Users must comply with any applicable legislation and/or testing requirements for the finished article, and are responsible for bringing their products to market.

This publication does not constitute any warranty, express or implied, and is intended only for the recipient and cannot therefore be transferred to any third party. We cannot assume any liability for the use of our products in conjunction with other materials.

All our products are sold subject to UPM Raflatac's general sales conditions, and you should ensure that any existing laws are observed.

This publication replaces all previous versions. All information is subject to change without notice.