

TeraPrint Produktunterlage

Gebrandete TeraPrint-Downloadunterlage

PRODUKT	Doppelseitiges Klebeband
UNTERLAGE	Datasheet
TYP	datasheet
ORIGINALSEITEN	1
STAND	16.06.2026
DATEI	products/ds-tape/assets/documents/57c0d48983d54ffa4cae73e06c7bff0b397bbd0f83246f41d9f3e767eef75f59.pdf

Wichtig fuer die Produktion

Die folgenden Originalseiten bleiben in Format, Reihenfolge und Inhalt unveraendert.
Druckmass, Schnitt, Beschnitt, Sicherheitsbereiche und technische Vorlage wurden nicht veraendert.
Bei Zertifikaten, Datenblaettern und Pruefberichten bleiben Aussteller und Originalinhalte unveraendert.

TeraPrint Hinweis

Diese Datei ist lokal bei TeraPrint gespeichert und fuer den Kunden-Download vorbereitet.
Bitte bei Druckdaten immer die Massangaben und Beschnitt-/Sicherheitszonen der Originalvorlage beachten.
Bei Unsicherheit vor Bestellung oder Produktion TeraPrint kontaktieren.



POLYPROPYLENE FILM TAPE

13600 is a double sided tape consisting of a polypropylene carrier, an acrylic adhesive and a siliconized paper. This tape has high initial adhesive properties. It is designed for bonding a wide range of substrates such as stainless steel, polyethylene and polypropylene.

Construction

Adhesive	Modified cross-linked solvent acrylic
Carrier	Polypropylene Transparent
Liner	Siliconized paper Brown

Applications

Fixing of fitting floorings and trims.
 Mounting of heavy decorative materials and displays.
 Suitable for bounding plastic moldings and metal materials.
 Mounting automotive applications, such as interior panels and outside mirrors.
 Mounting of signs and scales.
 General assembly applications (point-of-sales material, advertising, ...).

Technical details

Thickness	0,21 mm
Adhesive strength	27 N/25 mm
Service temperature range	-40°C to +80°C
Short term temperature	+150°C
Solvent resistance	Good
UV resistance	Good
Humidity resistance	Good
Dynamic shear	6 kg/cm ²
Static shear	1000g/3,23cm ² for 7 days at 23°C

Recommendations for use

Temperature: between +18°C and +25°C. Surface must be clean and free from dust and grease. Avoid touching exposed adhesive surface of the tape, as this impairs the performance. Pressure sensitive adhesive must be applied with a maximum of pressure in order to achieve maximum pressure level. The indicated level of performance will be reached after a bonding period of 24HRS at +23°C.

Storage and shelf life

Clean and dry in a well ventilated area, preferably at a temperature between +21°C and +38°C. Stored under these conditions shelf life will be a minimum of 24 months.

The above information is given in good faith, but the user should assure himself that the performance of the product is sufficient for his application. The quoted values are average and should not be taken as maximum or minimum values for specific purposes. Option Tape Specialties cannot be held responsible for product failure unless full testing has been carried out. The client has to decide on the tapes suitability for their own applications.



OPTION TAPE SPECIALTIES

Frankrijkstraat 8
 9140 Temse - Belgium
 Tel. : +32 (0)3 710 19 19 - Fax : +32 (0)3 711 34 64
 info@optiontapespecialties.com - www.optiontapespecialties.com