

TeraPrint Produktunterlage

Gebrandete TeraPrint-Downloadunterlage

PRODUKT	Flag PET
UNTERLAGE	Datenblatt Flag-PET
TYP	datasheet
ORIGINALSEITEN	2
STAND	16.06.2026
DATEI	products/flag-pet/assets/documents/9b352cd24269a302ff9fca649280e9cca7b90ac14f58d8db5101408b518f61b3.pdf

Wichtig fuer die Produktion

Die folgenden Originalseiten bleiben in Format, Reihenfolge und Inhalt unveraendert.
Druckmass, Schnitt, Beschnitt, Sicherheitsbereiche und technische Vorlage wurden nicht veraendert.
Bei Zertifikaten, Datenblaettern und Pruefberichten bleiben Aussteller und Originalinhalte unveraendert.

TeraPrint Hinweis

Diese Datei ist lokal bei TeraPrint gespeichert und fuer den Kunden-Download vorbereitet.
Bitte bei Druckdaten immer die Massangaben und Beschnitt-/Sicherheitszonen der Originalvorlage beachten.
Bei Unsicherheit vor Bestellung oder Produktion TeraPrint kontaktieren.

Technical Data Sheet

updated
checked

02.02.2017
02.02.2017

Product	Re-Jetflag GS PES-Fahnenstoff mit "INKTeX+® GS Ausrüstung" 6144RCGS made of REvive Polyester, because of the Recyling-process the degree of whiteness differs from production lot to production lot
Material	100% recycled Polyester
Stock widths	app. 320 cm
Making-up	rolled on paper cores
Packaging	wrapped with foil
Ecology	according to Öko-Tex Standard 100, product class IV
Ink-type	transfer printing, direct printing with dye-sub inks
Eigenschaften	Flame retardant

Weight				
acc. to DIN EN 12127	110.00	[g/m²]	+ - 5	[%]

Shrinkage

Heat Shrinkage, 195 °C, 90 sec, lengthwise				
acc. to PA0_13	-1.00	[%]	+ - 1	[%]
Heat Shrinkage, 195 °C, 90 sec, crosswise				
acc. to PA0_13	-1.00	[%]	+ - 1	[%]

Tearing strength

Elongation at 100 N, longitudinal direction				
acc. to DIN EN ISO 13934-1	5.00	[%]	+ - 20	[%]
Elongation at 100 N, cross direction				
acc. to DIN EN ISO 13934-1	20.00	[%]	+ - 20	[%]
Maximum tensile elongation, longitudinal direction				
acc. to DIN EN ISO 13934-1	30.00	[%]	+ - 20	[%]

Maximum tensile elongation, cross direction

acc. to DIN EN ISO 13934-1

50.00 [%]

+ - 20 [%]

Maximum tearing strength, longitudinal direction

acc. to DIN EN ISO 13934-1

min. 320.00 [N/5 cm]

Maximum tearing strength, cross direction

acc. to DIN EN ISO 13934-1

min. 540.00 [N/5 cm]

We do not accept liability for errors. Printing mistakes and changes are reserved.

Please pay attention to our general considerations regarding fabrication at www.g-o-friedrich.com

Page 2 / 2