

TeraPrint Produktunterlage

Gebrandete TeraPrint-Downloadunterlage

PRODUKT	Beachflag wave
UNTERLAGE	Datenblatt Flag Longlife
TYP	datasheet
ORIGINALSEITEN	2
STAND	16.06.2026
DATEI	products/mini-beachflag/assets/documents/9d6e9298cbc5dec09b24b53d3271ddcf4a36d54be4bfc63337cfb2fbc3e8965a.pdf

Wichtig fuer die Produktion

Die folgenden Originalseiten bleiben in Format, Reihenfolge und Inhalt unveraendert.
Druckmass, Schnitt, Beschnitt, Sicherheitsbereiche und technische Vorlage wurden nicht veraendert.
Bei Zertifikaten, Datenblaettern und Pruefberichten bleiben Aussteller und Originalinhalte unveraendert.

TeraPrint Hinweis

Diese Datei ist lokal bei TeraPrint gespeichert und fuer den Kunden-Download vorbereitet.
Bitte bei Druckdaten immer die Massangaben und Beschnitt-/Sicherheitszonen der Originalvorlage beachten.
Bei Unsicherheit vor Bestellung oder Produktion TeraPrint kontaktieren.

Technical Data Sheet

updated
checked

11.04.2023
11.04.2023

Product	8543K PES-FLAGFABRIC
Material	100 % Polyester
Stock widths	app. 310 cm
Making-up	rolled on paper cores
Packaging	wrapped with foil
Ecology	according to STANDARD 100 by OEKO-TEX, product class 2 (direct contact with skin)
Ink-type	transfer printing, screen printing, direct printing with dye-sub inks
Bleaching	do not bleach
Ironing	Ironing with low temperature
Washing	40° Machine wash, normal
Drying	tumbler dry with low temperature (gently)
Professional textile cleaning	professional dry-cleaning



Weight				
acc. to DIN EN 12127	106.00	[g/m ²]	+ - 3	[%]
Shrinkage				
Heat Shrinkage, 195 °C, 90 sec, lengthwise				
acc. to AA 25-02	-3.00	[%]	+ - 1	[%]

Heat Shrinkage, 195 °C, 90 sec,
crosswise

acc. to AA 25-02	-0.50	[%]	+ - 1	[%]
------------------	-------	-----	-------	-----

Tearing strength

Elongation at 100 N, longitudinal direction

acc. to DIN EN ISO 13934-1	8.00	[%]	+ - 20	[%]
----------------------------	------	-----	--------	-----

Elongation at 100 N, cross direction

acc. to DIN EN ISO 13934-1	32.00	[%]	+ - 20	[%]
----------------------------	-------	-----	--------	-----

Maximum tensile elongation, longitudinal
direction

acc. to DIN EN ISO 13934-1	30.00	[%]	+ - 20	[%]
----------------------------	-------	-----	--------	-----

Maximum tensile elongation, cross direction

acc. to DIN EN ISO 13934-1	62.00	[%]	+ - 20	[%]
----------------------------	-------	-----	--------	-----

Maximum tearing strength, longitudinal
direction (min.)

acc. to DIN EN ISO 13934-1	min. 250.00	[N/5 cm]		
----------------------------	-------------	----------	--	--

Maximum tearing strength, cross direction (min.)

acc. to DIN EN ISO 13934-1	min. 380.00	[N/5 cm]		
----------------------------	-------------	----------	--	--

We do not accept liability for errors. The confirmed properties are valid in the state of delivery. Any further processing can change them (e.g. washing / flame retardancy).

Please pay attention to our general considerations regarding fabrication at www.g-o-friedrich.com

Printing mistakes and changes are reserved.