

# TeraPrint Produktunterlage

Gebrandete TeraPrint-Downloadunterlage

|                |                                                                                                              |
|----------------|--------------------------------------------------------------------------------------------------------------|
| PRODUKT        | Motocrossaufkleber                                                                                           |
| UNTERLAGE      | Datenblatt Schlagfester Aufkleber                                                                            |
| TYP            | datasheet                                                                                                    |
| ORIGINALSEITEN | 1                                                                                                            |
| STAND          | 16.06.2026                                                                                                   |
| DATEI          | products/sticker-cross/assets/documents/3812fd055a6f377f6e53ee3eb31b35fc22b2cef47c4da96f0fc2acb3c63f54b2.pdf |

## Wichtig fuer die Produktion

Die folgenden Originalseiten bleiben in Format, Reihenfolge und Inhalt unveraendert.  
Druckmass, Schnitt, Beschnitt, Sicherheitsbereiche und technische Vorlage wurden nicht veraendert.  
Bei Zertifikaten, Datenblaettern und Pruefberichten bleiben Aussteller und Originalinhalte unveraendert.

## TeraPrint Hinweis

Diese Datei ist lokal bei TeraPrint gespeichert und fuer den Kunden-Download vorbereitet.  
Bitte bei Druckdaten immer die Massangaben und Beschnitt-/Sicherheitszonen der Originalvorlage beachten.  
Bei Unsicherheit vor Bestellung oder Produktion TeraPrint kontaktieren.

## TITAN FLOW | TFW-100

High tack satin white print vinyl with micro channel liner developed for long term applications on powervehicles.

### FACE FILM

Polymeric PVC, satin white

|                                       |      |                |
|---------------------------------------|------|----------------|
| Thickness (µm)                        | 100  |                |
| Tensile strength (N/mm <sup>2</sup> ) | >22  | EN ISO 527-3   |
| Elongation at break (%)               | >150 | DIN EN ISO 527 |

### ADHESIVE

Clear solvent-based acrylic, high tack permanent

|                          |    |             |
|--------------------------|----|-------------|
| Thickness (µm)           | 40 |             |
| Adhesion to steel        |    | FINAT FTM 1 |
| 20 minutes (180°) N/25mm | 30 |             |
| 24 hours (180°) N/25mm   | 35 |             |

### RELEASE LINER

Structured lay-flat kraft paper liner, double-sided PE-coated

|              |     |
|--------------|-----|
| Weight (gsm) | 140 |
|--------------|-----|

### PRODUCT APPLICATION

|                              |           |
|------------------------------|-----------|
| Application method           | Dry       |
| Application temperature (°C) | 10 to 30  |
| Service temperature (°C)     | -20 to 70 |

### DURABILITY

|                            |    |                                        |
|----------------------------|----|----------------------------------------|
| Shelf life (months)        | 12 |                                        |
| Outdoor durability (years) | 8  | Northern-EU climate, vertical exposure |

### ROLL SIZES

1370mm x 50m

1520mm x 50m

### PRINTING METHOD

(Eco)-Solvent, Latex, UV

Fourbases BV guarantees the material for twelve months from the date of final invoice. The shelf life of our material depends on storage conditions. The end user should store the material in the original boxes or in equivalent boxes, away from direct sunlight, at a temperature of 21°C and 50% relative humidity. Fourbases BV guarantees that the products are free from defects in workmanship or defects in TITAN material, provided they are stored properly. At its sole discretion, Fourbases BV may either: (1) replace all or part of the materials, or (2) issue a credit note for the value of the defective portion. All quoted data values are typical and should not be used as a basis to consider the product defective if measured values differ.