

# TeraPrint Produktunterlage

Gebrandete TeraPrint-Downloadunterlage

|                |                                                                                                                     |
|----------------|---------------------------------------------------------------------------------------------------------------------|
| PRODUKT        | Palettenabdeckung                                                                                                   |
| UNTERLAGE      | Datenblatt Dekostoff                                                                                                |
| TYP            | datasheet                                                                                                           |
| ORIGINALSEITEN | 2                                                                                                                   |
| STAND          | 16.06.2026                                                                                                          |
| DATEI          | products/straight-pop-up-wall/assets/documents/26488b894502971929ce67d949962947967f4b12cca86441f8d29742848e7024.pdf |

## Wichtig fuer die Produktion

Die folgenden Originalseiten bleiben in Format, Reihenfolge und Inhalt unveraendert.  
Druckmass, Schnitt, Beschnitt, Sicherheitsbereiche und technische Vorlage wurden nicht veraendert.  
Bei Zertifikaten, Datenblaettern und Pruefberichten bleiben Aussteller und Originalinhalte unveraendert.

## TeraPrint Hinweis

Diese Datei ist lokal bei TeraPrint gespeichert und fuer den Kunden-Download vorbereitet.  
Bitte bei Druckdaten immer die Massangaben und Beschnitt-/Sicherheitszonen der Originalvorlage beachten.  
Bei Unsicherheit vor Bestellung oder Produktion TeraPrint kontaktieren.

## Technical Data Sheet

updated  
checked

04.04.2023  
04.04.2023

**Product** **DecoTex GFS**  
PES-Dekotex mit "INKTeX+® FL Ausrüstung"  
7048GFS

**Material** 100 % Polyester

**Stock widths** app. 160 cm, 183 cm, 203 cm, 210 cm, 225 cm, 253 cm,  
260 cm, 266 cm, 310 cm, 320 cm, 328 cm, 410 cm,  
505 cm

**Making-up** rolled on paper cores

**Packaging** wrapped with foil

**Ecology** according to STANDARD 100 by OEKO-TEX,  
product class 2  
(direct contact with skin)

**Ink-type** transfer printing,  
direct printing with dye-sub inks,  
direct printing with UV curing inks,  
direct printing with HP Latex inks

**characteristics** Flame retardant

|                      |        |        |       |     |
|----------------------|--------|--------|-------|-----|
| Weight               |        |        |       |     |
| acc. to DIN EN 12127 | 220.00 | [g/m²] | + - 3 | [%] |

### Shrinkage

|                                               |       |     |       |     |
|-----------------------------------------------|-------|-----|-------|-----|
| Heat Shrinkage, 195 °C, 90 sec,<br>lengthwise |       |     |       |     |
| acc. to PA0_13                                | -2.50 | [%] | + - 1 | [%] |

|                                              |       |     |       |     |
|----------------------------------------------|-------|-----|-------|-----|
| Heat Shrinkage, 195 °C, 90 sec,<br>crosswise |       |     |       |     |
| acc. to PA0_13                               | -2.50 | [%] | + - 1 | [%] |

### Tearing strength

|                                             |       |     |        |     |
|---------------------------------------------|-------|-----|--------|-----|
| Elongation at 100 N, longitudinal direction |       |     |        |     |
| acc. to DIN EN ISO 13934-1                  | 25.00 | [%] | + - 20 | [%] |

|                                      |      |     |        |     |
|--------------------------------------|------|-----|--------|-----|
| Elongation at 100 N, cross direction |      |     |        |     |
| acc. to DIN EN ISO 13934-1           | 4.50 | [%] | + - 20 | [%] |

Maximum tensile elongation, longitudinal direction

acc. to DIN EN ISO 13934-1 80.00 [%] +- 20 [%]

Maximum tensile elongation, cross direction

acc. to DIN EN ISO 13934-1 45.00 [%] +- 20 [%]

Maximum tearing strength, longitudinal direction (min.)

acc. to DIN EN ISO 13934-1 min. 350.00 [N/5 cm]

Maximum tearing strength, cross direction (min.)

acc. to DIN EN ISO 13934-1 min. 1100.00 [N/5 cm]

Continuing tearing strength, longitudinal direction

acc. to DIN EN ISO 13937-2 28.00 [N] +- 10 [%]

Continuing tearing strength, cross direction

acc. to DIN EN ISO 13937-2 18.00 [N] +- 10 [%]

## others

Air Permeability

Measuring Pressure: 200 Pa

Testing Area: 20 cm<sup>2</sup>

acc. to DIN EN ISO 9237 598.00 [l/m<sup>2</sup> s] +- 10 [%]

We do not accept liability for errors. The confirmed properties are valid in the state of delivery. Any further processing can change them (e.g. washing / flame retardancy).

Please pay attention to our general considerations regarding fabrication at [www.g-o-friedrich.com](http://www.g-o-friedrich.com)

Printing mistakes and changes are reserved.