

TeraPrint Produktunterlage

Gebrandete TeraPrint-Downloadunterlage

PRODUKT	Wandaufkleber
UNTERLAGE	Datenblatt Roughmark
TYP	datasheet
ORIGINALSEITEN	1
STAND	16.06.2026
DATEI	products/wall-sticker/assets/documents/cad89f1f737cc7fbe936d1224fbb619aceab689091a6d13736a324e50b8106c2.pdf

Wichtig fuer die Produktion

Die folgenden Originalseiten bleiben in Format, Reihenfolge und Inhalt unveraendert.
Druckmass, Schnitt, Beschnitt, Sicherheitsbereiche und technische Vorlage wurden nicht veraendert.
Bei Zertifikaten, Datenblaettern und Pruefberichten bleiben Aussteller und Originalinhalte unveraendert.

TeraPrint Hinweis

Diese Datei ist lokal bei TeraPrint gespeichert und fuer den Kunden-Download vorbereitet.
Bitte bei Druckdaten immer die Massangaben und Beschnitt-/Sicherheitszonen der Originalvorlage beachten.
Bei Unsicherheit vor Bestellung oder Produktion TeraPrint kontaktieren.

Concept® 285 RoughMark™ is a 3.5 mil matte opaque polymeric vinyl film coated with a high-tack removable (HTR) acrylic pressure sensitive adhesive on a 90# layflat liner. The 90# liner provides excellent dimensional stability for digital printing. Concept® 285 accepts a variety of solvent-based, eco-solvent, latex and *UV curable inks common to wide format digital printing systems.

Applications Concept® 285 RoughMark™ can be used in applications where a conformable removable vinyl is desired. This film conforms well with controlled heat and features clean removability from a variety of moderately textured substrates including brick, block, and concrete surfaces (vertical application only). If a high gloss finish is desired, it is recommended to use Concept® 242 gloss clear cast laminate.

NOTE: If applied to a painted surface the paint must bond tightly to the substrate. Test all applications prior to use. Not designed for coated/ sealed/ treated stainless steel, brass or bronze surfaces

Thickness	Film	3.5 mils.
	Adhesive	1.8 to 2.1 mils.
	Liner	6.5 mils.
	(Thickness variation +/- 10%)	

Temperature Ranges	Minimum application temperature	+40°F.
	Service temperature	-40°F to +200 F.

Removability Removable up to 6 months for common substrates under normal exposure conditions.

Adhesion	Stainless steel	16 Oz/ inch minimum
	PSTC-101 Method A	
	Dwell is 24 hours at room temperature.	

Solvent Resistance Good resistance to intermittent exposure from petroleum oils, grease, aliphatic hydrocarbons and gasoline.

Water Resistance Excellent.

Humidity Resistance Excellent.

Storage Stability One year shelf life stored at 70° F and 50% relative humidity.

Recommendations Completely evaporate inkjet solvents before application. Failure to do so may facilitate solvent penetration resulting in vinyl degradation. * For UV Curable inks, please consult with the ink manufacturer for specifics on ink flexibility.

Product Codes	285-54	54" x 150'
	285-5475	54" x 75'
	285-60	60" x 150'
	285-6075	60" x 75'



*Manufacturer of Pressure Sensitive Films,
Traffic Graphic Floor Advertising Films, Custom
Coatings and Printing Inks.*